

What is claimed is:

1. A tray for a vapor phase step in which a heat-resistant thermosetting resin is intimately bonded and impregnated
5 to/into surfaces, including inner pore wall surfaces, of an inorganic continuously porous sintered body having a thickness of 0.5 to 10 mm and an open porosity of 5 to 50 % and a thin film of a super heat-resistant thermoplastic resin is formed thereon.
- 10 2. The tray according to claim 1,
wherein the inorganic continuously porous sintered body is selected from the group consisting of an aluminum nitride-boron nitride (AlN-h-BN) composite, an aluminum
15 nitride-silicon carbide-boron nitride (AlN-SiC-h-BN) composite, a silicon nitride-boron nitride ($\text{Si}_3\text{N}_4\text{-h-BN}$) composite, an alumina-boron nitride ($\text{Al}_2\text{O}_3\text{-h-BN}$) composite, β -silicon carbide ($\beta\text{-SiC}$) and wollastonite.
- 20 3. The tray according to claim 1,
wherein the heat-resistant thermosetting resin is selected from resins whose cured products have a thermal decomposition starting temperature of at least 400 °C and the heat-resistant thermoplastic resin is selected from resins
25 which have a thermal decomposition starting temperature of at least 500 °C.
4. A process for the production of a tray for a vapor phase step, comprising surface-treating an inorganic
30 continuously porous sintered body having a thickness of 0.5 to 10 mm and an open porosity of 5 to 50 % for resin impregnation, impregnating the inorganic continuously porous sintered body

with a thermosetting resin to intimately bond the thermosetting resin to surfaces thereof including inner pore wall surfaces, machining the sintered body into a predetermined tray shape, impregnating the machined sintered body with a solution of a super heat-resistant thermoplastic resin as a final impregnation, and subjecting the sintered body to heating, drying and heat-treatment to form a thin super heat-resistant thermoplastic resin layer.

5. A process for the production of a tray for a vapor phase step, comprising impregnating an inorganic continuously porous sintered body having an open porosity of 5 to 50 % with a thermally decomposable resin, cutting the sintered body to a thickness of 0.5 to 10 mm, then machining the sintered body into a predetermined tray shape, decomposing and removing the thermally decomposable resin, cleaning the sintered body, surface-treating the sintered body for heat-resistant resin impregnation, impregnating the sintered body with a heat-resistant thermosetting resin to intimately bond the resin to surfaces thereof including inner pore wall surfaces, further impregnating the sintered body with a solution of a super heat-resistant thermoplastic resin, and subjecting the sintered body to heating, drying and heat-treatment to form a thin super heat-resistant thermoplastic resin layer.

25

6. The process according to claim 4 or 5, wherein the surface-treatment for heat-resistant resin impregnation is a surface-treatment including the inner pore wall surfaces in which an organic metal compound solution is impregnated, air-dried, dried, heated and thermally decomposed.

30